



V60 ARCHITECTURAL GRADE SILICONE

NEUTRAL CURE

06 December 2017

YOUR SMART ADVANTAGES

- Bostik V60 is a premium grade neutral cure glazing weatherproofing silicone sealant
- Its superior adhesion to painted and anodized aluminum & glass has made this silicone the market leader in the glass market for the last 25 years
- The thixotropic nature of this product ensures that it will not slump in typical construction joints
- Excellent U.V. Stability
- Long Life Reliability
- Bostik V60 has excellent natural ageing stability. It will maintain its elastomeric joint sealant properties permanently, even under harsh conditions and temperature extremes.

DESCRIPTION

Bostik V60 is a high performance architectural grade Glazing silicone. One component, non-flowing, Neutral cure, High modulus sealant. It cures by absorption of atmospheric moisture to form a flexible and durable elastomeric sealant.

USES

- Two sided structural glazing. (Colours only on to aluminum substrate)
- Structurally glazed systems. (Subject to Bostik approval and review of design first).
- Fin Glazing. (all V60 colours including trans).
- Sealing of Laminated and reflective glass
- General glazing applications
- Sealing of mirrors and splash backs (not vinyl backed)
- Toughened Glass Assemblies
- Weather Sealing in curtain walls and building facades
- Weather Sealing of composite metal panels
- Drinking Water – tank manufacturing.

CLASSIFICATIONS/STANDARDS

Bostik V60 Silicone Glazing Sealant meets or exceeds the requirements of the following specification for a one – part sealant:

- AS-1288:2006
- ASTM C1184, Type S, Use G and O.
- C920: Type S Grade NS, Class 35, Use NT, A, G, O.
- GB-16776
- Meets Low VOC Rating – 47g/L (SCAQMD)
- AS/NZS4020-2005 – Drink water approved AWQC (Trans & Grey Only)
- ASTM C792

PRODUCT CHARACTERISTICS

Colour	Translucent, White, Grey, Black, Silver & Matt Black
Tack Free Time	30 Minutes
Skin Time	8 Minutes
Tooling Time	8 Minutes
Slag or Slump	Nil
Coverage	Approximately 16 lineal metres per 300ml cartridge based on an average joint size of 6mm depth and 3mm width

Product code	
300ml cartridge/20 per ctn	
Translucent	30804561
White	30840201
Grey	30840214
Black	30804555
Silver	30840556
Matt Black	30840229
600ml sausages/20 per ctn	
Translucent	30610925

TYPICAL PERFORMANCE DATA (approx.)

Shore "A" hardness	22
100% Modulus	0.5 MPa
Tensile Strength	1.5 MPa
Elongation	500%
Peel Strength after UV through Glass	89N/25mm
Dynamic Movement Capacity	±35%
Accelerated Aging and Weathering (ASTM C792)	Excellent

V60 ARCHITECTURAL GRADE SILICONE NEUTRAL CURE

Application temperature*	-10°C to 40°C
--------------------------	---------------

Service temperature	-50 to 200°C
---------------------	--------------

* Application of the sealant at -10°C is permissible provided the surface to receive the silicone is dry and free of frost. The maximum service temperature listed is for transient temperature; the silicone sealant will deteriorate if subjected to these temperatures on a continuous basis.

APPLICATION INSTRUCTIONS SURFACE PREPARATION

Surfaces to be sealed must be clean, dry and free of wax, grease, cutting oils or any loose or flaking materials.

Use the two-wipe process for impervious substrates. Ensure the cloths are clean and changed frequently, and use a suitable cleaner/solvent such as IPA or 100% White Spirits.

APPLICATION

When extruding the sealant cut the nozzle to the desired width, cut the tip off the cartridge, and apply the sealant firmly to ensure good contact between the sealant and the substrate.

Before the sealant has skinned, tool it off to ensure a good finish, and to improve the wetting out of the sealant to the substrate.

Clean / wipe off excess sealant with clean cloth or polyethylene scraper. Masking tape can be used. (Masking tape must be removed before skin over starts).

JOINT DESIGN

The sealant must be capable of withstanding the expected joint movement.

To calculate the joint width, establish the expected movement (expansion, contraction and shear movement) that the joint is required to withstand. The joint movement capability of **Bostik V60** is $\pm 35\%$. The joint design must avoid three-sided adhesion. The recommended sealant depth to width ratio for a weather seal is normally half the joint width.

The minimum recommended joint depth is 6mm and the maximum is 15mm, ideally if the required joint width is 6mm the depth is also 6mm.

There is a separate formula for structural glazing. (Please contact our sales office for details).

(No warranty will be given for Bostik V60, on structural glazing and other applications unless Bostik has reviewed all detail drawings of the project, and a signed copy of the joint design and substrate testing has been approved by Bostik before commencing any projects.)

V60 is recommended to be used only for 2 sided structural glazing including Fin glazing, refer to Bostik for 4 sided structural scenarios.

BACK UP MATERIAL

Use a closed cell polyethylene-backing rod, 25% larger than the joint width, to control the depth of the joint.

COMPATIBILITY WITH ADJACENT SUBSTRATES

Silicones are not always compatible with plasticized sealants, such as butyls.

Also some backing rods and glazing tapes contain bitumen or other agents that are incompatible with the silicone.

The incompatibility may cause discoloration, poor sealant cure or long term degradation of the sealant. Always carry out compatibility tests where contact with potentially incompatible materials occurs. (Bostik offers this service via our labs facilities for projects.)

COVERAGE

Approximately 16 lineal metres per 300ml cartridge based on an average joint size of 6mm depth and 3mm width.

CURING TIME

Bostik V60 cures by absorbing atmospheric moisture it will cure 2-3mm in the first 24hrs and to a depth of 7mm in 7 days.

Depending on the joint design it may take between 14-21 days before the silicone joint has fully cured. (Subject to temperature and atmospheric moisture) Lower atmospheric moisture reduces the curing rate.

LIMITATIONS

BOSTIK V60 is ***NOT*** suitable for use in the following applications:-

- As the sealant requires atmospheric humidity to cure, it will not cure in totally confined spaces where it does not have access to atmospheric humidity.
- Aquariums
- Under Water Applications on concrete, some plastic materials etc. (including swimming pools)
- **Note.** This product is suitable for some under water non porous substrates applications where the sealant is in contact with water for extended periods eg metal tanks. (Please contact Bostik to confirm your design details before commencing such an application).
- Some stones. (Use Bostik 5CLM - we recommend the completion of a stain testing program before using sealant on stone)
- Below Grade Applications
- Horizontal walkways.
- Do not clean or treat the sealant with materials, cleaning agents or solvents, that may affect or discolour the sealant, particularly during product curing.
- Polycarbonate sheeting
- Sealant may discolour copper and brass.
- This product is neither tested nor can be used for medical or pharmaceutical use.
- Where building materials may bleed oil, plasticisers or solvents, some vulcanized rubbers and tapes.

V60 ARCHITECTURAL GRADE SILICONE NEUTRAL CURE

- Surfaces subject to corrosion / oxidation -eg mill aluminum.
- **This silicone is not paintable.**

If there is a requirement to paint the sealant, use Bostik MS or PU sealant or Bostik Fill-A-Gap acrylic sealant products. Refer to Technical Data Sheet of product for appropriate application and follow both the sealant and paint manufacturers painting instructions carefully, when painting these sealants.

Bostik Co-operative Test Program

Effective sealant systems require the sealant to adhere to the substrates, and work in the joint without cohesive failure.

The intention of the program is to eliminate potential problems by pre-testing sealants with actual samples of the building materials to be used.

This test will provide detailed information about optimum surface preparation techniques, including recommendations for cleaning substrates, (cleaners / solvents) if required.

We will also review the shop drawings - proposed joint designs for potential failures, such as three-sided adhesion, and requirements for wind or dead load systems.

For projects that incorporate stone substrates, we test (Stain Test) because of the variability of stone's, in terms of porosity and texture, we carry out these tests before commencement of each project. (Test samples for stain test should be the same as will be used on the building).

To commence a test program contact your local Bostik office

STORAGE & SHELF LIFE

Always store the sealant in a cool dry place. Ideal storage temperature is not more than 25°C. Prolonged storage at high temperatures may affect shelf life and ultimate performance. The shelf life of **Bostik V60** is 12 months from the date of manufacture when stored below 23°C and below 50% relative humidity.

HEALTH & SAFETY

Full product safety information required for safe use is not included in this data sheet. Before handling, read the separate Safety Data Sheet (SDS) and packaging for safe use. Always read the Technical Data Sheet and Safety Data Sheet (SDS) before opening or using this product.

In case of product emergency refer to product labelling or SDS and contact phone numbers. A copy of the product SDS is available from Bostik or its distributors.
FIRST AID

If accidentally swallowed or it gets into someone eyes, contact a Doctor or Poisons Information Centre (Phone Australia 131 126; New Zealand 0800 764 766)

SEE THE MATERIAL SAFETY DATA SHEET FOR ADDITIONAL INFORMATION.

EMERGENCY INFORMATION: 1800 033 111 (ALL HOURS)

Important Notice for Users

Suggestions for use should not be taken as an inducement to infringe any particular patent.

***Bostik V60 is a registered trademark of Bostik Australia.**

(Structural testing for Bostik V60 carried out by Bostik & independent company).

BOSTIK HOTLINE

Smart help 1800 898 551



This datasheet is for the general help of users. It is provided in good faith. The data is current and accurate to the best of our knowledge. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. Users should carry out tests to decide the product's suitability for purpose. This data sheet and the properties of the product may change without notice. Users, suppliers and retailers should check that the data sheets they have are the latest. To the maximum extent permitted by law, Bostik disclaims all warranties in relation to manufacture and use of the product. Bostik is not liable for representations made by users, suppliers or retailers about the product. Bostik is not liable for any loss or damage resulting from incorrect, careless, or negligent use or storage of the product, including use of out of date product. Any liability arising from use of the product is limited to the replacement or purchase price of the product. Bostik does not exclude rights and remedies that cannot be excluded by legislation, for example under the Australian Consumer Law (ACL). Sale of the product by Bostik is subject to the Bostik Australia Proprietary Limited Conditions and Terms of Sale. For more information on Bostik, products, and conditions of use and sale visit www.bostik.com/au